

The Curves of Material & Characteristics FT600 Materials(NiZn)

Material	Initial Permeability	Relative Loss Factor	Relative Temperature Coefficient	Saturation Magnetic Flux Density	Reman-ence	Coercivity	Curie Temperature	Electrical Resistivity	Applied Frequency Range	Density
Unit symbol	μ_i $\pm 20\%$	$\tan \delta/\mu_i$ $\times 10^{-6}$	$\alpha \mu_i \gamma$ $\times 10^{-4}$	B_s (MT)	B_r (MT)	H_C (A/m)	T_c (°C)	ρ ($\Omega \cdot m$)	F MHz	d g/cm ³
FT600	600	45 (0.1MHz)	16 - 21	310 (1600A/m)	150	40	>160	>10 ⁵	3 - 13	4.5

