

The Curves of Material & Characteristics FT750 Materials(NiZn)

Material	Initial Permeability	Relative Loss Factor	Relative Temperature Coefficient	Saturation Magnetic Flux Density	Reman-ence	Coercivity	Curie Temperature	Electrical Resistivity	Applied Frequency Range	Density
Unit symbol	μ_i $\pm 20\%$	$\tan \delta/\mu$ $\times 10^{-4}$	$\alpha \mu, \gamma$ $\times 10^{-6}$	Bs (MT)	Br (MT)	HC (A/m)	Tc (°C)	ρ ($\Omega \cdot m$)	F MHz	d g/cm ³
FT750	750	45 (0.1MHz)	0 - 50	330 (1600A/m)	150	35	> 140	> 10 ⁵	0.1 - 2	4.7

