

The Curves of Material & Characteristics FT1.5K Materials(NiZn)

Material	Initial Permeability	Relative Loss Factor	Relative Temperature Coefficient	Saturation Magnetic Flux Density	Reman-ence	Coercivity	Curie Temperature	Electrical Resistivity	Applied Frequency Range	Density
Unit symbol	μ_i $\pm 20\%$	$\tan \delta / \mu_i$ $\times 10^{-6}$	$\alpha \mu_i \gamma$ $\times 10^{-4}$	Bs (MT)	Br (MT)	HC (A/m)	Tc (°C)	ρ ($\Omega \cdot m$)	F MHz	d g/cm ³
FT1.5K	1500	23 (0.1MHz)	2 - 4	280 (1600A/m)	100	10	>105	>10 ⁵	0.01 - 0.5	5.0

